

Cycolac* Resin GSE

Americas: LIMITED USE

ABS, all purpose extrusion grade. Excellent toughness, good formability, high gloss and good stiffness.

Property

TYPICAL PROPERTIES ⁽¹⁾			
	Value	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	44	MPa	ASTM D 638
Tensile Modulus, 5 mm/min	2200	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	75	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2270	MPa	ASTM D 790
Hardness, Rockwell R	105	-	ASTM D 785
IMPACT			
Izod Impact, notched, 23°C	373	J/m	ASTM D 256
Falling Dart Impact, 23°C	25	J	SABIC Method
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	95	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	97	°C	ASTM D 648
CTE, -40°C to 40°C, flow	9.54E-05	1/°C	ASTM E 831
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
PHYSICAL			
Specific Gravity	1.04	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.5 - 0.8	%	SABIC Method
Melt Flow Rate, 230°C/3.8 kgf	2.5	g/10 min	ASTM D 1238
OPTICAL			
Gloss, untextured, 60 deg (sheet)	90	-	ASTM D 523
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	4	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating (3)	1.47	mm	UL 94
UV-light, water exposure/immersion	F2	-	UL 746C

Source GMD, last updated:12/29/1999

Processing

- Recommend initial lower temperatures settings to avoid material degradation/hang-up in die.

Parameter	Value	Unit
Sheet Extrusion		
Drying Temperature	80 - 95	°C
Drying Time	4	hrs
Maximum Moisture Content	0 - 0.02	%

Melt Temperature	215 - 260	°C
Barrel - Zone 1 Temperature	170 - 200	°C
Barrel - Zone 2 Temperature	180 - 220	°C
Barrel - Zone 3 Temperature	190 - 225	°C
Barrel - Zone 4 Temperature	200 - 240	°C
Adapter Temperature	205 - 250	°C
Die Temperature	205 - 250	°C
Roll Stack Temp - Top	90 - 95	°C
Roll Stack Temp - Middle	95 - 105	°C
Roll Stack Temp - Bottom	100 - 105	°C

Source GMD, last updated:12/29/1999

- Purge material from extruder prior to shutdown.

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR [\(LOCAL SALES OFFICE\)](#) FOR AVAILABILITY IN YOUR REGION

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

Disclaimer : THE MATERIALS AND PRODUCTS OF THE BUSINESSES MAKING UP THE SABIC INNOVATIVE PLASTICS COMPANY, ITS SUBSIDIARIES AND AFFILIATES ("SABIC IP"), ARE SOLD SUBJECT TO SABIC IP' S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SABIC IP MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SABIC IP MATERIALS, PRODUCTS, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SABIC IP' S STANDARD CONDITIONS OF SALE, SABIC IP AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS OR PRODUCTS DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of SABIC IP' s materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating SABIC IP materials or products will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of SABIC IP' s Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by SABIC IP. No statement contained herein concerning a possible or suggested use of any material, product or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product or design in the infringement of any patent or other intellectual property right

* Cicolac is a trademark of the SABIC Innovative Plastics Company

© 1997-2008 SABIC Innovative Plastics Company.All rights reserved