

## Lexan\* Resin LI1911R

Americas: COMMERCIAL

Low-viscosity multi-purpose PC having low levels of ionics species. Internal mold release.

### Property

TYPICAL PROPERTIES <sup>(1)</sup>			
	Value	Unit	Standard
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	68	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	7	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	125	%	ASTM D 638
Tensile Modulus, 5 mm/min	2380	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	96	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2340	MPa	ASTM D 790
Hardness, Rockwell R	118	-	ASTM D 785
Taber Abrasion, CS-17, 1 kg	10	mg/1000cy	ASTM D 1044
Tensile Stress, yield, 50 mm/min	63	MPa	ISO 527
Tensile Stress, break, 50 mm/min	65	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	100	%	ISO 527
Tensile Modulus, 1 mm/min	2350	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	90	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
<b>IMPACT</b>			
	Value	Unit	Standard
Izod Impact, unnotched, 23°C	3204	J/m	ASTM D 4812
Izod Impact, notched, 23°C	694	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	62	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	12	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eU
<b>THERMAL</b>			
	Value	Unit	Standard
Vicat Softening Temp, Rate B/50	154	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	125	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	137	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	129	°C	ASTM D 648
CTE, -40°C to 95°C, flow	6.84E-05	1/°C	ASTM E 831
Specific Heat	1.25	J/g-°C	ASTM C 351
Thermal Conductivity	0.19	W/m-°C	ASTM C 177
CTE, 23°C to 80°C, flow	7.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	7.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	PASS	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	140	°C	ISO 306
Vicat Softening Temp, Rate B/120	141	°C	ISO 306
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	122	°C	ISO 75/Ae
<b>PHYSICAL</b>			
	Value	Unit	Standard
Specific Gravity	1.2	-	ASTM D 792

Specific Volume	0.83	cm <sup>3</sup> /g	ASTM D 792
Density	1.19	g/cm <sup>3</sup>	ASTM D 792
Water Absorption, equilibrium, 100°C	0.58	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.5 - 0.7	%	SABIC Method
Melt Flow Rate, 300°C/1.2 kgf	17.5	g/10 min	ASTM D 1238
Density	1.2	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/sat)	0.35	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 220°C/5.0 kg	21	cm <sup>3</sup> /10 min	ISO 1133
OPTICAL	Value	Unit	Standard
Light Transmission	88	%	ASTM D 1003
Haze	1	%	ASTM D 1003
Refractive Index	1.586	-	ASTM D 542

Source GMD, last updated:08/03/2004

## Processing

Parameter	Value	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	48	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	280 - 305	°C
Nozzle Temperature	275 - 300	°C
Front - Zone 3 Temperature	280 - 305	°C
Middle - Zone 2 Temperature	270 - 295	°C
Rear - Zone 1 Temperature	260 - 280	°C
Mold Temperature	70 - 95	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	40 - 70	rpm
Shot to Cylinder Size	40 - 60	%
Vent Depth	0.025 - 0.076	mm

Source GMD, last updated:08/03/2004

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR [\(LOCAL SALES OFFICE\)](#) FOR AVAILABILITY IN YOUR REGION

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

**Disclaimer :** THE MATERIALS AND PRODUCTS OF THE BUSINESSES MAKING UP THE SABIC INNOVATIVE PLASTICS COMPANY, ITS SUBSIDIARIES AND AFFILIATES ("SABIC IP"), ARE SOLD SUBJECT TO SABIC IP' S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SABIC IP MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SABIC IP MATERIALS, PRODUCTS, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SABIC IP' S STANDARD CONDITIONS OF SALE, SABIC IP AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING

FROM ANY USE OF ITS MATERIALS OR PRODUCTS DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of SABIC IP' s materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating SABIC IP materials or products will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of SABIC IP' s Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by SABIC IP. No statement contained herein concerning a possible or suggested use of any material, product or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product or design in the infringement of any patent or other intellectual property right

\* Lexan is a trademark of the SABIC Innovative Plastics Company

© 1997-2008 SABIC Innovative Plastics Company.All rights reserved