

LNP* Thermocomp* Compound RF004XXH


Americas: COMMERCIAL

Also known as: LNP* Thermocomp* Compound RF-1004 HC

Product reorder name: RF004XXH

LNP THERMOCOMP* RF004XXH is a compound based on Nylon 66 resin containing Glass Fiber. Characteristic of this grade is Healthcare.

| TYPICAL PROPERTIES ¹ | TYPICAL VALUE | Unit | Standard |
|---|---------------|---------------------|-------------|
| MECHANICAL | | | |
| Tensile Stress, break | 1590 | kgf/cm ² | ASTM D 638 |
| Tensile Strain, break | 3.6 | % | ASTM D 638 |
| Tensile Modulus, 50 mm/min | 73100 | kgf/cm ² | ASTM D 638 |
| Flexural Stress | 2350 | kgf/cm ² | ASTM D 790 |
| Flexural Modulus | 59700 | kgf/cm ² | ASTM D 790 |
| Tensile Stress, break | 159 | MPa | ISO 527 |
| Tensile Strain, break | 3.7 | % | ISO 527 |
| Tensile Modulus, 1 mm/min | 7300 | MPa | ISO 527 |
| Flexural Stress | 241 | MPa | ISO 178 |
| Flexural Modulus | 7000 | MPa | ISO 178 |
| IMPACT | | | |
| Izod Impact, unnotched, 23°C | 84 | cm-kgf/cm | ASTM D 4812 |
| Izod Impact, notched, 23°C | 10 | cm-kgf/cm | ASTM D 256 |
| Instrumented Impact Energy @ peak, 23°C | 116 | cm-kgf | ASTM D 3763 |
| Multiaxial Impact | 25 | cm-kgf | ISO 6603 |
| Izod Impact, unnotched 80*10*4 +23°C | 56 | kJ/m ² | ISO 180/1U |
| Izod Impact, notched 80*10*4 +23°C | 8 | kJ/m ² | ISO 180/1A |
| THERMAL | | | |
| HDT, 0.45 MPa, 3.2 mm, unannealed | 260 | °C | ASTM D 648 |
| HDT, 1.82 MPa, 3.2mm, unannealed | 247 | °C | ASTM D 648 |
| CTE, -40°C to 40°C, flow | 3.78E-05 | 1/°C | ASTM E 831 |
| CTE, -40°C to 40°C, xflow | 7.92E-05 | 1/°C | ASTM E 831 |
| CTE, -40°C to 40°C, flow | 3.88E-05 | 1/°C | ISO 11359-2 |



(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23±176.C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.
 (3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.
 (4) Internal measurements according to UL standards.
 (5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

Source GMD, last updated:

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA.

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right. SABIC Innovative Plastics is a trademark of SABIC Holding Europe B.V.

* LNP is a trademark of SABIC Innovative Plastics IP BV

* Thermocomp is a trademark of SABIC Innovative Plastics IP BV

© 1997-2011 SABIC Innovative Plastics Holding BV. All rights reserved

LNP* Thermocomp* Compound RF004XXH

Americas: COMMERCIAL

| TYPICAL PROPERTIES ¹ | TYPICAL VALUE | Unit | Standard |
|---------------------------------------|---------------|--|----------------------|
| THERMAL | | | |
| CTE, -40°C to 40°C, xflow | 7.94E-05 | 1/°C | ISO 11359-2 |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm | 221 | °C | ISO 75/Af |
| PHYSICAL | | | |
| Density | 1.295 | g/cm ³ | ASTM D 792 |
| Moisture Absorption, 50% RH, 24 hrs | 0.8 | % | ASTM D 570 |
| Mold Shrinkage, flow, 24 hrs (5) | 0.5 | % | ASTM D 955 |
| Mold Shrinkage, xflow, 24 hrs (5) | 1.2 | % | ASTM D 955 |
| Mold Shrinkage, flow, 24 hrs (5) | 0.47 | % | ISO 294 |
| Mold Shrinkage, xflow, 24 hrs (5) | 1.24 | % | ISO 294 |
| Wear Factor Washer | 80 | 10 ⁻⁴ -10 in ³ -min/ft-lb-hr | ASTM D 3702 Modified |
| Dynamic COF | 0.68 | - | ASTM D 3702 Modified |
| Static COF | 0.52 | - | ASTM D 3702 Modified |
| Density | 1.29 | g/cm ³ | ISO 1183 |



(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23±176.C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

Source GMD, last updated:

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA.

DISCLAIMER : THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com>. AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed Seller. No statement Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right. SABIC Innovative Plastics is a trademark of SABIC Holding Europe B.V.

* LNP is a trademark of SABIC Innovative Plastics IP BV

* Thermocomp is a trademark of SABIC Innovative Plastics IP BV

© 1997-2011 SABIC Innovative Plastics Holding BV. All rights reserved

LNP* Thermocomp* Compound RF004XXH

Americas: COMMERCIAL

| PROCESSING PARAMETERS | TYPICAL VALUE | Unit |
|-----------------------------|---------------|------|
| Injection Molding | | |
| Drying Temperature | 80 | °C |
| Drying Time | 4 | hrs |
| Maximum Moisture Content | 0.15 - 0.25 | % |
| Melt Temperature | 280 - 305 | °C |
| Front - Zone 3 Temperature | 295 - 305 | °C |
| Middle - Zone 2 Temperature | 280 - 295 | °C |
| Rear - Zone 1 Temperature | 265 - 275 | °C |
| Mold Temperature | 95 - 110 | °C |
| Back Pressure | 0.2 - 0.3 | MPa |
| Screw Speed | 30 - 60 | rpm |



(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23±176.C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

Source GMD, last updated:

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA.

DISCLAIMER : THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com>. AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED. (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed Seller. No statement Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right. SABIC Innovative Plastics is a trademark of SABIC Holding Europe B.V.

* LNP is a trademark of SABIC Innovative Plastics IP BV

* Thermocomp is a trademark of SABIC Innovative Plastics IP BV

© 1997-2011 SABIC Innovative Plastics Holding BV. All rights reserved